

# DUCKBACK®

## Slip - Resistant Textured Coating

# 3200 Series

## 50 VOC



### General Description

**SUPERDECK® SLIP-RESISTANT COATING** is a high build elastomeric coating designed to offer slip resistance to wood and concrete stairs, ramps, decks, docks, patios, sidewalks and more. The slip-resistant additive is built into this ready to use formula. The unique formula provides long lasting protection against moisture and the damaging effects of the sun. It is designed to expand and contract along with the substrate while offering excellent scuff resistance for heavy duty foot traffic areas. The coating is specially formulated to resist growth of mildew and algae on the coating's surface.

### Recommended Substrates

New or old exterior wood or concrete ramps, balconies, porches, stairs, walkways, as well as wood decking, boat docks, plywood decking, and composite decking. Note: not for use on garage floors, driveways, or automobile traffic areas. Product will fill cracks up to 1/4" making it ideal for resurfacing old damaged wood decking and concrete patios. For cracks greater than 1/4" use Duckback® Seam Tape to bridge gaps.

### Tinting & Base Color Information

Ready Mix Colors. Do not tint.

SC 3201-WHITE  
SC 3202-ADOBE  
SC 3203-RED  
SC 3204-BROWN  
SC 3205-GREEN  
SC 3206-GRAY

### Features / Benefits

- Ready to use formula
- Foot friendly grip
- Provides a slip-resistant surface

### Product Application

#### **SURFACE PREPARATION:**

All surfaces must be clean, dry, and free from dirt, mildew stains, dust and other foreign matter. Do not apply over sealed surfaces. For wood surfaces remove surface stains, dirt and failed oxidized stains with Superdeck® Wood Cleaner. Remove all loose peeling paint, rinse thoroughly with water and allow to completely dry before coating. For concrete surfaces do not apply to smooth concrete, use Mason's Select® Concrete Etcher and follow instructions for etching concrete surfaces.

**WARNING!** Removal of old paint by sanding, scraping, or other means may generate dust or fumes that may contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information call the National Lead Information Center at 1-800-424- LEAD (in US) or contact your local health authority.

#### **PRODUCT PREPARATION:**

Shake well or stir thoroughly from bottom to top of container and occasionally during application. When using more than one container of product, intermix all containers to ensure color consistency. Test small area first for color satisfaction.

#### **THINNING:**

Do not thin.

#### **APPLICATION METHODS:**

Apply a thick coat with brush or roller. When rolling use 3/8" nap synthetic roller cover for light texture finishes, 1/2"-3/4" nap for medium texture finish, and 1-1/4" nap for heavy texture finishes. Back rolling is suggested when spraying working the product smoothly and evenly into the surface to ensure a



## Product Application (cont.)

uniform appearance. Always maintain a wet edge to avoid lapping. Test Area: Always apply product to a small test area and allow to dry completely before coating entire project to ensure desired color and appearance.

### SLIP RESISTANT:

This product meets recommended standards set forth by the Americans with Disabilities Act (ADA) for slip resistant surfaces.

### APPLICATION TEMPERATURE:

50°F.–90°F. Do not apply product in extreme heat of day or if surface is hot to touch. Do not apply product if rain is likely to occur within 24 hours.

### DRY TIME @ 77°F:

1 Hour to touch. Allow surface to dry until it can be lightly walked on (2–4 hours) before recoating. Once the final coat has been applied allow 24–48 hours dry time for normal foot traffic. Dry time may be prolonged in cooler temperatures or high humidity. Surface may remain tacky until fully dried and cured. Avoid using surface until fully dry. Due to the elastomeric nature and high build of this product, full dry and cure time may take a few days.

### SPREAD RATE:

Coverage may vary on surface condition, type of surface and number of coats applied. On most wood and concrete surfaces the coverage will be about 100 square feet per gallon for application of 1–2 coats. When filling deep cracks in concrete or locking down splinters on old extremely damaged wood surfaces additional coats may be needed.

### MAINTENANCE:

Apply one new coat every 5–7 years to a clean surface to renew color and maintain durability. Use Superdeck® Wood Cleaner and follow maintenance instructions before recoating.

### CLEAN UP:

Clean brushes and equipment with soap and water. Dispose of empty container or unused portion in accordance with local, state, and federal regulations.

## Physical Properties

<i>DENSITY:</i>	10.86–11.19 lbs/gal
<i>SPECIFIC GRAVITY:</i>	1.30–1.34 (depending on color)
<i>VISCOSITY:</i>	107–113 KU
<i>SOLIDS % WEIGHT:</i>	55–58 % (depending on color)
<i>SOLIDS % VOLUME:</i>	42–44 % (depending on color)
<i>FLASH POINT:</i>	None
<i>V.O.C.:</i>	<50 grams per liter
<i>ANTI-SLIP ADDITIVE:</i>	Glass Oxide
<i>COEFFICIENT OF FRICTION:</i>	1.18 dry surface, 1.02 wet surface

### OTHER:

#### SC 3201 Slip-Resistant Coating White

<u>CAS Number</u>	<u>Ingredient</u>
7732-18-5	Water
Proprietary	Acrylic Polymer
65997-17-3	Glass
12736-96-8	Nepheline Syenite
13463-67-7	Titanium Dioxide
NON-PHOTOCHEMICALLY REACTIVE	
VOC: 43 g/L – 0.36 lb/gal as per 40 CFR 59.406	

#### SC 3202 Slip-Resistant Coating Adobe

<u>CAS Number</u>	<u>Ingredient</u>
7732-18-5	Water
Proprietary	Acrylic Polymer
65997-17-3	Glass
12736-96-8	Nepheline Syenite
13463-67-7	Titanium Dioxide
1333-86-4	Carbon Black
NON-PHOTOCHEMICALLY REACTIVE	
VOC: 44 g/L – 0.37 lb/gal as per 40 CFR 59.406	

#### SC 3203 Slip-Resistant Coating Red

<u>CAS Number</u>	<u>Ingredient</u>
7732-18-5	Water
Proprietary	Acrylic Polymer
65997-17-3	Glass
12736-96-8	Nepheline Syenite
1309-37-1	Iron Oxide
13463-67-7	Titanium Dioxide
NON-PHOTOCHEMICALLY REACTIVE	
VOC: 45 g/L – 0.38 lb/gal as per 40 CFR 59.406	



## Physical Properties (cont.)

### SC 3204 Slip-Resistant Coating Brown

<u>CAS Number</u>	<u>Ingredient</u>
7732-18-5	Water
Proprietary	Acrylic Polymer
65997-17-3	Glass
12736-96-8	Nepheline Syenite
51274-00-1	Iron Oxide

NON-PHOTOCHEMICALLY REACTIVE  
VOC: 45 g/L – 0.37 lb/gal as per 40 CFR 59.406

### SC 3205 Slip-Resistant Coating Green

<u>CAS Number</u>	<u>Ingredient</u>
7732-18-5	Water
Proprietary	Acrylic Polymer
65997-17-3	Glass
12736-96-8	Nepheline Syenite
51274-00-1	Iron Oxide

NON-PHOTOCHEMICALLY REACTIVE  
VOC: 42 g/L – 0.35 lb/gal as per 40 CFR 59.406

### SC 3206 Slip-Resistant Coating Gray

<u>CAS Number</u>	<u>Ingredient</u>
7732-18-5	Water
Proprietary	Acrylic Polymer
65997-17-3	Glass
12736-96-8	Nepheline Syenite
13463-67-7	Titanium Dioxide

NON-PHOTOCHEMICALLY REACTIVE  
VOC: 44 g/L – 0.37 lb/gal as per 40 CFR 59.406

## Cautions

**CAUTIONS:** Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **WARNING:** This product contains chemicals known to

## Cautions (cont.)

the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**

01/10 (15)

## Conformance

OTC Approved:	Yes
SCAQMD Approved:	Yes
LADCO Approved:	Yes
CARB Approved:	Yes
ASTM Standard:	N/A
Master Painters Institute (MPI):	N/A

## Packaging

1-Gallon Container - 124 fl oz (3<sup>7</sup>/<sub>8</sub> U.S. Qt) 3.66 L  
5-Gallon Container - 620 fl oz (4<sup>27</sup>/<sub>32</sub> U.S. Gal) 18.3 L

## Limited Warranty

If this product, when applied according to label instructions to a properly prepared surface, fails to perform in accordance with applicable product literature, manufacturer shall, upon presentation of proof of purchase to manufacturer or its authorized representative, either replace an equivalent quantity of product free of charge or refund the original purchase price. This warranty shall not apply to any defect or damage resulting from improper surface preparation, structural defects, or failure of a previous product. This is your sole remedy under this warranty. To obtain performance under this warranty, contact manufacturer at (800) 825-5382 or superdeck.com. You may be asked to contact the retailer from whom you purchased this product for further warranty instructions. THIS WARRANTY EXCLUDES (1) LABOR OR COSTS ASSOCIATED WITH LABOR FOR THE APPLICATION OR REMOVAL OF ANY PRODUCT, AND (2) ANY INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Some states do not allow the exclusion or limitation of incidental or consequential damages, so the above limitation or exclusion may not apply to you. This warranty gives you specific legal rights, and you may have other rights, which vary from state to state.

